DTF WASH CARE CHECKLIST

Wait to Wash:
Let your newly pressed garment sit for 24 to 48 hours before its first wash. This curing period ensures the adhesive permanently and fully bonds with the fabric fibers.

Turn Inside Out:
Always flip the garment inside out before putting it in the wash. This protects the printed side from direct friction with the machine drum and other clothing.

Use Cold Water:
Keep water temperatures below 86°F (30°C). Hot water can melt or soften the DTF adhesive over time, which causes peeling.

Gentle Cycle & Mild Detergent:
Select a delicate cycle to minimize harsh agitation. Use a mild, color-safe liquid detergent. Avoid harsh chemicals, bleach, or industrial-strength stain removers.

Avoid Fabric Softeners:
Fabric softeners contain chemicals that break down the adhesive backing of DTF transfers, which leads to cracking and early deterioration.

Drying:
Air drying or hang drying is the best option for longevity. If you must use a machine, select the tumble dry low setting.Ironing Cautions: Never iron directly on the design. If you need to iron the garment, turn it inside out and use a low heat setting, or use a pressing cloth as a barrier.